



Technical Report No. 68.140.13.068.01 Rev.001

Dated 2013-03-29

- Client: Name: Shenzhen Clear Lighting Co., Ltd
Address: Bldg. 2, Guanlong Industrial Zone, Xili, 518055 Shenzhen,
PEOPLE'S REPUBLIC OF CHINA
Contact Person: Mr. Guo
- Manufacturing place: Manufacturer's name: Shenzhen Clear Lighting Co., Ltd
Address: Bldg. 2, Guanlong Industrial Zone, Xili, 518055 Shenzhen,
PEOPLE'S REPUBLIC OF CHINA
Factory's name: Same as manufacturer
Address: Same as manufacturer
- Test subject: Product: LED Neon Ribbon Light; LED Crystal Ribbon Light
Type: C-FR-F10, C-FR-F11, C-FR-F15X(X=A, B or S), C-FR-F21X(X=A, B or S),
C-FR-F22, C-FR-F05, C-FR-F07 [for LED Neon Ribbon Light];
C-FR-F16X(X=A or S), C-FR-F17 [for LED Crystal Ribbon Light]
- Test specification: 1, Needle flame test according to clause 13.3.1 of EN 60598-1:2008+A1:2009;
2, Glow-wire test according to clause 13.3.2 of EN 60598-1:2008+A1:2009.
- Purpose of examination:
- inspection according to specified requirements to realize the conformity with the Produktsicherheitsgesetz –ProdSG, version Nov 08, 2011
 - inspection according to specified requirements to realize the observance of the protection aims of the following EC directives:
 - LVD directive 2006/95/EC
 - EMC directive 2004/108/EC
 - Test according to the test specification.
- Test result: The test results show that the presented products are in compliance with the test specification.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

1 Description of the test subject

1.1 Function

- Manufacturer's specification for intended use:
The materials used in LED light.

1.2 Consideration of the foreseeable misuse

- Not applicable
 Covered through the applied standard
 Covered by the following comment
 Covered by attached risk analysis

1.3 Technical Data

Nil.

2 Order

2.1 Date of Purchase Order, Customer's Reference

2013-03-19

2.2 Receipt of Test Sample, Location

20pcs samples were received on 2013-03-20, TEC Department, Shenzhen

2.3 Date of Testing

2013-03-20 to 2013-03-26

2.4 Location of Testing

TEC Department, Shenzhen

2.5 Points of Non-compliance or Exceptions of the Test Procedure

Nil.

3 Test results

3.1 Needle flame test (clause 13.3.1 of EN 60598-1)

Test condition

The test process is as follows:

- a) The test specimens, the wooden board and the tissue paper were conditioned 24 h in an atmosphere having a temperature between 15 °C and 35 °C and a relative humidity between 45 % and 75 % before starting the test.
- b) A piece of flat smooth wooden board, approximately 10 mm thick covered in close contact with a single layer of wrapping tissue, is positioned at a distance of 200 mm ± 5 mm below the place where the needle-flame is applied to the test specimen. Wrapping tissue as specified in 4.215 of ISO 4046-4 is a soft and strong, lightweight wrapping tissue 12 g/m² to 30 g/m².
- c) Mounted the specimen, maintained an 8 mm spacing between the centre of the top of the burner and the remaining portion of the test specimen.
- d) The burner was tilted up to 45° from the vertical, and the test flame was applied to the specimen for 10 s at the point where the highest temperatures are likely to occur.

Test Result: Pass

Model No.	Applying needle flame time (s)	Duration of buring (s) (after 10s needle flame)	Observation	Result
C-FR-F10	10	0	No buring drop	Pass
C-FR-F11	10	1.3	No buring drop	Pass
C-FR-F15X(X=A,B or S)	10	0.9	No buring drop	Pass
C-FR-F21X(X=A,B or S)	10	1.6	No buring drop	Pass
C-FR-F22	10	0	No buring drop	Pass
C-FR-F05	10	0	No buring drop	Pass
C-FR-F07	10	0.9	No buring drop	Pass
C-FR-F16X(X=A or S)	10	2	No buring drop	Pass
C-FR-F17	10	2	No buring drop	Pass

3.2 Glow-wire test (clause 13.3.2 of EN 60598-1)

Test condition

- a) The wooden board and the tissue paper were conditioned 24 h in an atmosphere having a temperature between 15 °C and 35 °C and a relative humidity between 45 % and 75 % before starting the test.
- b) A piece of flat smooth wooden board, approximately 10 mm thick covered in close contact with a single layer of wrapping tissue, is positioned at a distance of 200 mm ± 5 mm below the place where the glow-wire is applied to the test specimen. Wrapping tissue as specified in 4.215 of ISO 4046-4 is a soft and strong, lightweight wrapping tissue 12 g/m² to 30 g/m².
- c) The specimen was mounted so that the planar area of the surface was vertical and the tip of the glow-wire was applied to the centre of the planar area of the surface.
- d) The glow-wire was heated to the specified temperature (650 °C), the tip of the glow-wire was then brought slowly into contact with the test specimen for 30 s.
- e) The penetration of the tip of the glow-wire into and through the test specimen was limited to 7 mm ± 0,5 mm.

Test Result: Pass

Model No.	Applying glow-wire time (s)	Duration of burning (s) (after 30s glow-wire)	Observation	Result
C-FR-F10	30	0	No burning and molten drop	Pass
C-FR-F11	30	0	No burning and molten drop	Pass
C-FR-F15X(X=A,B or S)	30	0	No burning and molten drop	Pass
C-FR-F21X(X=A,B or S)	30	0	No burning and molten drop	Pass
C-FR-F22	30	0	No burning and molten drop	Pass
C-FR-F05	30	0	No burning and molten drop	Pass
C-FR-F07	30	0	No burning and molten drop	Pass
C-FR-F16X(X=A or S)	30	0	No burning and molten drop	Pass
C-FR-F17	30	0	No burning and molten drop	Pass



4 Remark

4.1 Annex 1: photo document.

5 Documentation

Nil.

6 Summary

The test specification is met.

**Jiangsu TÜV Product Service Ltd. Shenzhen Branch
TÜV SÜD Group**


Engineer: Sunny Yan
Sunny Yan
Project Handler



Technical Report checked: Taylor Yao
Taylor Yao
Designated Reviewer

Annex 1: Photo document

Details of: Outlook view



Details of: Outlook view

